


ZIBO JINGGAN REFRACTORY IMPORT AND EXPORT CO.,LTD

Address:NO. 3, Yanhe Road, Boshan, Zibo, Shandong, China
Email:wp@cnjingganrefractory.com/sdwenping@163.com
Contact:Rose Tel/Wechat:+86-13275332819
Tel:86-533-4188518 Fax:86-533-4188518

Direct-bond Magnesite Chrome Brick



1,Product description:

1,Direct-bond Magnesite Chrome Brick is made of high purity sintered magnesia and chromite with $\text{SiO}_2 < 2\%$ and sintered at high temperature ($1750 \sim 1800^\circ\text{C}$). The product is composed of periclase and magnesia-chromium spinel as the main crystalline phase.

2,Direct-bond Magnesite Chrome Brick has few impurities, direct combination of crystalline phase and crystalline phase, low porosity, high compressive strength, strong wear resistance, corrosion resistance, thermal shock resistance and spalling resistance.

3, Application of Direct-bond Magnesite Chrome Brick: Widely used in electric arc furnace, copper smelting furnace, refining furnace, cement rotary kiln.

4,Index:

ITEM		JD-12	JD-20
MgO	%	>60	>55
Cr ₂ O ₃	%	12	20
SiO ₂	%	<2	<1.6
Porosity	%	≤ 18	≤ 17
B.D	g/cm ³	>3.0	>3.1
Cold crushing strength	Mpa	>50	>55

ZIBO JINGGAN REFRACTORY IMPORT AND EXPORT CO.,LTD

Refractoriness under load	°C	>1650	>1700
Thermal expansion rate,1400°C,2hours	%	<0.8	<0.8
Thermal shock stability,950°C,air cooling,times		>50	>50

5.Good feedback of product use effect,the products have been exported to Oman, the United States, Morocco and India.

6.The manufacturer is a professional manufacturer and can provide complete product index test reports or third-party test reports.

Do you want to find a professional supplier of refractory products?

Do you want to find a professional supplier of graphite electrodes?

Do you want to find a stable and credible supplier?

Then let's contact with jinggan company

Contact me:

Email:wp@cnjingganrefractory.com/sdwenping@163.com

TEL: 86-0533-4188518 / FAX: 86-0533-4188518

Rose:+86-13275332819 (wechat/whatsapp number)